




FILMTEC Membranes

FILMTEC® 4.6" Tapwater RO Elements

Product Specifications

| Product | Product Water Flow Rate | | | Salt Rejection | |
|--------------------|-------------------------|---------------------|-------|----------------|-------------------|
| | (gpd) | (m ³ /d) | (l/h) | Minimum (%) | Typical Field (%) |
| TW30HP-4611 | 1200 | 4.54 | 189 | 97.5 | 99.0 |
| TW30-4619 | 1450 | 5.49 | 229 | 98.0 | 99.0 |
| TW30HP-4641 | 3800 | 14.38 | 599 | 97.5 | 99.0 |

1. Permeate flow and salt rejection based on the following test conditions: 2000 ppm NaCl, 225 psi (1.6 MPa), 77°F (25°C), pH 8, and recovery as indicated below.
2. Flow rates for individual elements may vary -15%/+25% for TW30-4619 and -15%/NUL (NUL: No Upper Limit) for TW30HP-4611 and TW30HP-4641.
3. Sales specification may vary slightly as design revisions take place.



Operating Limits

| | |
|--|---------------------|
| Membrane Type..... | Thin-Film Composite |
| Maximum Operating Pressure..... | 600 psi (4.1 MPa) |
| Maximum Feed Flow Rate | See note 4 |
| pH Range, Continuous..... | .2 to 11 |
| pH Range, Cleaning Cycle (30 min.) | .1 to 12 |
| Maximum Operating Temperature | 113° F (45 °C) |
| Maximum Feed Turbidity | .1 NTU |
| Maximum Feed Silt Density Index | SDI 5 |
| Free Chlorine Tolerance | <0.1 ppm |

| Single-Element Recovery (Permeate Flow to Feed Flow) | Recovery | Dimensions – Inches (mm) | | | |
|---|----------|--------------------------|-----------|-----------|------------|
| | | A | B | C | D |
| TW30-4611 | 0.05 | 11.45 (291) | 1.05 (27) | 0.75 (19) | 4.61 (117) |
| TW30-4619 | 0.08 | 19.30 (490) | – | 0.75 (19) | 4.61 (117) |
| TW30-4641 | 0.15 | 41.31 (1049) | 2.19 (55) | 0.75 (19) | 4.61 (117) |

4. Maximum Feed Flow: 13 gpm (3.0 m³/h) for TW30HP-4611 and 18 gpm (4.1 m³/h) for TW30-4619 and TW30HP-4641.
5. Element to fit 4.6-inch I.D. pressure vessel.

1 inch = 25.4 mm

*Trademark of The Dow Chemical Company

FILMTEC Membranes

For more information about FILMTEC membranes, call Dow Liquid Separations:

North America 1-800-447-4369
Latin America (+55) 11-5188-9345
Europe (+31) 20-691-6268
Japan (+81) 3-5460-2100
Australia (+61) 2-9776-3226
<http://www.dow.com/liquidseps>

Important Operating Information

1. Keep elements moist at all times after initial wetting.
2. If operating specifications given in this Product Information bulletin are not strictly followed, the limited warranty will be null and void.
3. Permeate obtained from first hour of operation should be discarded.
4. To prevent biological growth during storage, shipping or system shutdowns it is recommended that FILMTEC elements be immersed in a protective solution. The standard storage solution contains 1.5 percent (by weight) sodium metabisulfite (food grade).
5. Elements must be in use for at least six hours before formaldehyde is used as a biocide. If the elements are exposed to formaldehyde before being in use for this period of time, a loss in flux may result.
6. The membrane shows some resistance to short-term attack by chlorine (hypochlorite). Continuous exposure, however, may damage the membrane and should be avoided.
7. The customer is fully responsible for the effects of incompatible chemicals on elements. Their use will void the element limited warranty.

Notice: No freedom from any patent owned by Seller or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other governmental enactments. Seller assumes no obligation or liability for the information in this document. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.

Published August 1997.



*Trademark of The Dow Chemical Company

Form No. 609-00150-897QRP
CH 172-104-E-897